

CHEMICAL COMPATIBILITY FOR **100R7 & 100R8**

CHEMICAL PRODUCT	POLYESTER	POLYAMIDE 6	POLYAMIDE 12	POLYURETHANE
Formic Acid	B	C	C	C
Freon R 407C	A	A	-	C
Freon R134a	A	A	-	-
Gasoline	B	A	A	-
Glycerin	A	A	A	B
Glycolic Acid	-	C	-	-
Hexane	A	A	A	B
Hydrazine	C	-	-	C
Hydrochloric Acid, 10%	B	C	C	C
Hydrogen	A	A	A	A
Hydrogen Peroxide, 5%	-	C	B	-
Hydrogen Sulfide, 5%	A	C	C	-
Isooctane	A	A	A	B
Isopropyl Alcohol	A	A	B	-
Lactic Acid, 10%	-	B	A	-
Linseed Oil	A	A	A	-
Mercury	A	A	A	A
Methyl Alcohol	A	A	A	C
Methyl Chloride	C	C	C	C
Methyl Ethyl Ketone	B	A	A	C
Methylene Chloride	C	B	C	C
Mineral Oil	A	A	A	A
Naptha	A	A	A	C
Napthalene	B	A	A	B
Nitric Acid, 10%	B	C	C	C
Nitric Acid, 30%	C	C	C	C
NitrobenzenE	C	B	B	C
Nitromethane	-	A	A	-
Oil Fiat Tutela Lhm	A	-	-	-
Oil Kluber Summit Hy Syn Fg 22	A	-	-	-
Oil Panolin 9632	A	-	-	-
Oil Panolin Hlp Synth	A	-	-	-
Oil Pentosin Super Dot 4	-	A	A	-
Oleic Acid	A	A	A	B
Oleum, 20-25%	C	C	C	C
Palmitic Acid	A	A	-	A
Perchloric Acid, 10%	-	C	-	-
Perchloroethylene	C	A	A	C
Petrol	B	A	A	B
Phenol	C	C	C	C
Phosphoric Acid (10%)	-	C	-	-



TAIPAN

Email: sales@taipan.com.au
Fax: 07 5428 1311

CONTACT US 1300 654 782
www.taipan.com.au